

What is Claimed Is:

1. A photocurable resin composition comprising:
  - (A) a cationically polymerizable organic compound;
  - 5 (B) a cationic photopolymerization initiator;
  - (C) an ethylenically unsaturated monomer;
  - (D) a radical photopolymerization initiator; and
  - (E) a polyol.
- 10 2. The photocurable resin composition according to claim 1, wherein the composition comprises, relative to the total weight of the composition,
  - 20-85 wt% component (A),
  - 5-45 wt% component (C), and
  - 15 5-35 wt% component (E).
3. A photocurable resin composition according to any one of claims 1-2, wherein said component (A) comprises at least one compound having two or more  
20 alicyclic epoxy groups.
4. A photocurable resin composition according to any one of claims 1-3, wherein component (C) comprises  
25 at least one polyfunctional ethylenically unsaturated monomer.
5. A photocurable resin composition according to any one of claims 1-4, wherein component (E) comprises  
30 at least one polyether polyol having 3-6 hydroxyl groups.
6. The photocurable resin composition according to claims 1-5, wherein said composition further  
35 comprises elastomer particles.

7. The photocurable resin composition according to claim 6, wherein said elastomer particles have an average particle diameter of 10-700 nm.
- 5 8. A photocurable resin composition according to any one of claims 6-7, wherein the elastomer particles include core-shell particles.
- 10 9. A photocurable resin composition according to any one of claims 6-8, wherein the elastomer particles having a base component including polybutadiene, polyisoprene, styrene/butadiene copolymer, styrene/isoprene copolymer, ethylene/propylene copolymer, ethylene/olefin copolymer,  
15 ethylene/olefin/polyene copolymer, acrylic rubber, butadiene/(meth)acrylate copolymer, styrene/butadiene block copolymer, or styrene/isoprene block copolymer.
- 20 10. A photocurable resin composition according to any one of claims 6-9, wherein the elastomer particles include at least one core-shell particle having a partially crosslinked core comprising polybutadiene, polyisoprene, styrene/butadiene  
25 copolymer, styrene/isoprene copolymer, butadiene/(meth)acrylate copolymer, styrene/butadiene block copolymer, or styrene/isoprene block copolymer; and a shell comprising a methyl methacrylate polymer,  
30 methyl methacrylate/glycidyl copolymer, or methacrylate copolymer.
11. A photocurable resin composition according to any one of claims 1-10, wherein said composition  
35 further comprises an epoxy-branched alicyclic compound (G).

12. A photocurable resin composition according to claim 11, wherein said epoxy-branched alicyclic compound (G) comprises at least 2 epoxy-branched alicyclic groups.
- 5
13. A photocurable resin composition according to any one of claims 11-12, wherein said epoxy-branched alicyclic compound (G) comprises an epoxyethyl group.
- 10
14. A photocurable resin composition according to any one of claims 11-13, wherein said epoxy-branched alicyclic compound (G) comprises a residue of an organic compound having a valency of from 1-100.
- 15
15. A photocurable resin composition according to any one of claims 11-14, wherein said epoxy-branched alicyclic compound (G) comprises a residue of an organic compound linked via an oxy group to at least one epoxyalkyl-branched cycloalkyl group.
- 20
16. A photocurable resin composition according to any one of claims 11-15, wherein said epoxy-branched alicyclic compound (G) comprises an epoxyalkyl-branched cycloalkyl group that is hydroxy substituted.
- 25
17. A photocurable resin composition according to any one of claims 11-16, wherein said epoxy-branched alicyclic compound (G) includes a hydroxyepoxyethylcyclohexyl group.
- 30
18. A photocurable resin composition according to any one of claims 11-17, wherein said epoxy-branched alicyclic compound (G) includes a 1-hydroxy-3-(1,2-epoxyethyl)cyclohexyl group.
- 35

19. A process for photo-fabricating a three-dimensional object comprising:  
selectively curing a photo-curable resin according to any one of claims 1-18.

5

20. A three-dimensional object formed from a photocurable resin composition according to any one of claims 1-18, or with a process according to claim 19.